



# Chemical Resistance Chart for ARC Composites

Ambient temperature and maximum concentration apply, unless otherwise noted

	S1	S1HB	S2	S3	S4+	982	SD4i	5	10	855	858	890	BX1	897	BX2	MX1	MX2	MX3	MX4	MX5	CS2	CS4	791	988	
Aceton [CH <sub>3</sub> COCH <sub>3</sub> ]	4	4	3	2	2	2	3	3	3	3	3	3	3	3	3	3	3	3	2	4	4	3	3	2	
Acetylen [C <sub>2</sub> H <sub>2</sub> ]	3	3	2	2	1	1	2	2	2	2	2	2	2	2	2	2	2	2	1	3	4	1	1	1	
Aluminiumklorid(torr) [AlCl <sub>3</sub> ]	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	
Aluminiumsulfat(alun)[Al <sub>2</sub> (SO <sub>4</sub> ) <sub>3</sub> ]	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	
Alun [Al <sub>2</sub> (SO <sub>4</sub> ) <sub>3</sub> ]	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	
Ammoniumhydroxid(28%) [NH <sub>4</sub> OH]	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	2	1	1	1	
Ammoniumkarbonat[(NH <sub>4</sub> ) <sub>2</sub> CO <sub>3</sub> ]	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	
Ammoniumklorid [NH <sub>4</sub> Cl]	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	
Ammoniummonofosfat [(NH <sub>4</sub> )H <sub>2</sub> PO <sub>4</sub> ]	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	
Ammoniumnitrat [NH <sub>4</sub> NO <sub>3</sub> ]	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	
Ammoniumsulfat[(NH <sub>4</sub> ) <sub>2</sub> SO <sub>4</sub> ]	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	
Ammoniumvätekarbonat [NH <sub>4</sub> HCO <sub>3</sub> ]	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	
Avloppsvatten	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	
Bariumhydroxid[Ba(OH) <sub>2</sub> ]	1	1	1	1	1	1	1	2	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	
Bariumkarbonat [BaCO <sub>3</sub> ]	1	1	1	1	1	1	1	2	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	
Bariumklorid [BaCl <sub>2</sub> ]	1	1	1	1	1	1	1	2	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	
Bariumsulfat [BaSO <sub>4</sub> ]	1	1	1	1	1	1	1	2	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	
Bensin [C <sub>7</sub> H <sub>16</sub> /C <sub>10</sub> H <sub>22</sub> ]	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	2	1	2	1	
Bensol [C <sub>6</sub> H <sub>6</sub> ]	3	3	3	2	2	2	3	3	3	3	3	3	3	3	3	3	3	3	2	3	4	2	3	2	
Betsocker [C <sub>12</sub> H <sub>22</sub> O <sub>11</sub> ]	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	
Blyacetat [Pb(CH <sub>3</sub> COO) <sub>2</sub> ]	2	2	1	2	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	2	1	1	1	
Bunker C	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	
Butan [C <sub>4</sub> H <sub>10</sub> ]	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	
Butylen [C <sub>4</sub> H <sub>8</sub> ]	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	
Citronsyra(20%) [C <sub>6</sub> H <sub>8</sub> O <sub>7</sub> ]	3	3	2	2	1	1	2	3	2	2	2	2	2	2	2	2	2	2	2	1	2	4	1	2	1
Dejoniserat vatten [H <sub>2</sub> O]	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	
Dibutyladipat [C <sub>14</sub> H <sub>26</sub> O <sub>4</sub> ]	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	
Dibutylftalat[C <sub>16</sub> H <sub>22</sub> O <sub>4</sub> ]	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	
Dibutylsebacat[C <sub>18</sub> H <sub>34</sub> O <sub>4</sub> ]	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	
Dieselbränsle	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	
Dietylamin [C <sub>4</sub> H <sub>11</sub> N]	3	3	2	1	1	1	2	2	2	2	2	2	2	2	2	2	2	2	1	2	4	2	2	1	
Dioktylftalat [C <sub>24</sub> H <sub>40</sub> O <sub>4</sub> ]	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	

1= Continuous long term immersion  
2= Short term/intermittent immersion (<72 hrs.)

Chemical resistance Swedish.xls

3= Spills w/ immediate cleanup (<8 hrs.)  
4= Not recommended for direct contact



# Chemical Resistance Chart for ARC Composites

Ambient temperature and maximum concentration apply, unless otherwise noted

	S1	S1HB	S2	S3	S4+	982	SD4i	5	10	855	858	890	BX1	897	BX2	MX1	MX2	MX3	MX4	MX5	CS2	CS4	791	988
Dioktylsebacat[C26H52O4]	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1
Etan [C2H6]	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1
Etanol [CH3CH2OH]	2	2	2	1	1	1	2	2	3	2	2	2	2	2	2	2	2	1	2	3	2	3	2	2
Etylendiklorid [ClCH2CH2Cl]	4	4	4	3	3	3	4	4	4	4	4	4	4	4	4	4	3	3	4	4	3	4	3	3
Etylenglykol [HOCH2CH2OH]	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1
Etylenklorid [CH3CH2Cl]	4	4	4	3	3	3	4	4	4	4	4	4	4	4	4	4	3	3	4	4	3	4	3	3
Etylenoxid [C2H4O]	3	3	3	2	1	1	3	3	2	3	3	3	3	3	3	3	2	1	3	3	2	2	1	1
Fenoler [C6H6O]	4	4	4	4	2	2	4	4	4	4	4	4	4	4	4	4	3	2	4	4	3	4	2	2
Fluorkiselsyra (10%) [H2SiF6]	3	3	2	3	1	1	2	2	2	2	2	2	2	2	2	2	2	1	3	4	2	2	1	1
Fluorvätesyra (10%) [HF]	3	3	2	2	1	1	2	2	3	2	2	2	2	2	2	2	2	1	3	3	2	3	2	2
Flygbränsle	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	2	1	2	1	1
Formaldehyd(35%) [CH2O]	2	2	1	1	1	1	1	1	2	1	1	1	1	1	1	1	1	1	2	3	1	1	1	1
Fosforsyra(10%) [H3PO4]	3	3	2	3	1	1	2	2	2	2	2	2	2	2	2	2	2	1	3	3	2	1	1	1
Fosforsyra(30%) [H3PO4]	4	4	3	4	1	1	3	4	3	3	3	3	3	3	3	3	3	1	4	4	2	2	1	1
Fosforsyra(50%) [H3PO4]	4	4	3	4	1	1	3	4	3	3	3	3	3	3	3	3	3	1	4	4	4	3	1	1
Fosforsyra(85%) [H3PO4]	4	4	3	4	2	2	3	4	3	3	3	3	3	3	3	3	3	2	4	4	4	3	2	2
Fotogen	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1
Glukos [C6H12O6]	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1
Grönlut	1	1	1	1	1	1	1	1	2	1	1	1	1	1	1	1	1	1	1	2	1	1	1	1
Heptan [C7H16]	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1
Hexan [C6H14]	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1
Iso-oktan [C8H18]	2	2	2	1	1	1	2	2	2	2	2	2	2	2	2	2	1	1	2	3	1	1	1	1
Isopropylalkohol [C3H8O]	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1
Jetbränsle (JP-5)	1	1	1	1	1	1	1	1	2	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1
Järn(III)klorid(torr) [FeCl3]	2	2	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	2	2	1	1	1	1
Järn(III)nitrat [Fe(NO3)3]	2	2	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	2	3	1	1	1	1
Järn(III)sulfat [Fe2(SO4)3]	2	2	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	3	3	1	1	1	1
Järnklorid [FeCl2]	2	2	2	1	1	1	2	2	2	2	2	2	2	2	2	2	1	1	2	3	1	1	1	1
Järnnitrat [Fe(NO3)2]	2	2	1	1	1	1	1	1	2	1	1	1	1	1	1	1	1	1	2	2	1	1	1	1
Järnsulfat [FeSO4]	2	2	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	2	2	1	1	1	1
Kalciumbisulfit [Ca(HSO3)2]	3	3	2	2	1	1	2	2	2	2	2	2	2	2	2	2	2	1	2	3	1	1	1	1
Kalciumhydroxid [Ca(OH)2]	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1

1= Continuous long term immersion  
2= Short term/intermittent immersion (<72 hrs.)

Chemical resistance Swedish.xls

3= Spills w/ immediate cleanup (<8 hrs.)  
4= Not recommended for direct contact



# Chemical Resistance Chart for ARC Composites

Ambient temperature and maximum concentration apply, unless otherwise noted

	S1	S1HB	S2	S3	S4+	982	SD4i	5	10	855	858	890	BX1	897	BX2	MX1	MX2	MX3	MX4	MX5	CS2	CS4	791	988
Kalciumkarbonat [CaCO <sub>3</sub> ]	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1
Kalciumklorid [CaCl <sub>2</sub> ]	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1
Kalciumsulfat [CaSO <sub>4</sub> ]	1	1	1	1	1	1	1	2	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1
Kalialun [AlK <sub>2</sub> O <sub>8</sub> S <sub>2</sub> ]	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1
Kaliumbisulfat [KHSO <sub>4</sub> ]	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1
Kaliumbromid(30%) [KBr]	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1
Kaliumcyanid [KCN]	2	2	2	2	1	1	2	2	2	2	2	2	2	2	2	2	2	2	1	2	2	1	1	1
Kaliumdifosfat [K <sub>2</sub> HPO <sub>4</sub> ]	3	3	2	2	1	1	2	3	2	2	2	2	2	2	2	2	2	2	1	2	3	1	1	1
Kaliumdikromat [K <sub>2</sub> Cr <sub>2</sub> O <sub>7</sub> ]	3	3	2	3	2	2	2	3	2	2	2	2	2	2	2	2	2	3	2	2	3	2	3	2
Kaliumferricyanid [K <sub>3</sub> Fe(CN) <sub>6</sub> ]	2	2	1	2	1	1	1	2	1	1	1	1	1	1	1	1	1	1	1	1	2	1	1	1
Kaliumferrocyanid [K <sub>4</sub> Fe(CN) <sub>6</sub> ]	2	2	1	2	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	2	1	1	1
Kaliumhydroxid(10%) [KOH]	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1
Kaliumhydroxid(50%) [KOH]	2	2	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	2	1	1	1
Kaliumjodid [KI]	1	1	1	1	1	1	1	2	1	1	1	1	1	1	1	1	1	1	1	1	2	1	1	1
Kaliumkarbonat(50%) [K <sub>2</sub> CO <sub>3</sub> ]	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1
Kaliumklorid(30%) [KCl]	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1
Kaliumnitrat [KNO <sub>3</sub> ]	1	1	1	1	1	1	1	2	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1
Kaliumpermanganat [KMnO <sub>4</sub> ]	3	3	2	2	1	1	2	3	2	2	2	2	2	2	2	2	2	3	1	2	3	2	2	1
Kaliumvätekarbonat [KHCO <sub>3</sub> ]	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1
Kalkvatten [Ca(OH) <sub>2</sub> /H <sub>2</sub> O]	2	2	2	1	1	1	2	1	2	2	2	2	2	2	2	2	2	2	1	1	2	1	1	1
Karbamid [H <sub>2</sub> NCONH <sub>2</sub> ]	2	2	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	2	2	1	1	1
Klördioxid(12%) [ClO <sub>2</sub> ]	3	3	3	2	2	2	3	3	3	3	3	3	3	3	3	3	3	3	2	3	4	2	2	2
Koldioxid(torr) [CO <sub>2</sub> ]	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1
Kolmonoxid [CO]	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1
Kolsyra [H <sub>2</sub> CO <sub>3</sub> ]	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1
Kopparacetat [Cu(C <sub>2</sub> H <sub>3</sub> O <sub>2</sub> ) <sub>2</sub> ]	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1
Kopparklorid [CuCl]	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1
Kopparnitrat [Cu(NO <sub>3</sub> ) <sub>2</sub> ]	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1
Kopparsulfat [CuSO <sub>4</sub> ]	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1
Kromkaliumbisulfat[KCr(SO <sub>4</sub> ) <sub>2</sub> .12H <sub>2</sub> O]	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1
Kromsyra(10%) [H <sub>2</sub> Cr <sub>2</sub> O <sub>7</sub> ]	3	3	3	3	2	2	3	3	3	3	3	3	3	3	3	3	3	3	2	3	4	3	3	2
Kungsvatten [(HNO <sub>3</sub> )/3(HCl)]	4	4	4	4	2	2	4	4	4	4	4	4	4	4	4	4	4	4	2	4	4	4	4	3

1= Continuous long term immersion  
2= Short term/intermittent immersion (<72 hrs.)

Chemical resistance Swedish.xls

3= Spills w/ immediate cleanup (<8 hrs.)  
4= Not recommended for direct contact



# Chemical Resistance Chart for ARC Composites

Ambient temperature and maximum concentration apply, unless otherwise noted

	S1	S1HB	S2	S3	S4+	982	SD4i	5	10	855	858	890	BX1	897	BX2	MX1	MX2	MX3	MX4	MX5	CS2	CS4	791	988
Kvicksilver [Hg]	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1
Kvicksilverklorid [HgCl <sub>2</sub> ]	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1
Magnesiumbisulfat [Mg(HSO <sub>4</sub> ) <sub>2</sub> ]	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1
Magnesiumklorid [MgCl <sub>2</sub> ]	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1
Magnesiumsalt [MgSO <sub>4</sub> .7H <sub>2</sub> O]	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1
Magnesiumsulfat [MgSO <sub>4</sub> ]	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1
Maleinatsyra(30%) [C <sub>4</sub> H <sub>4</sub> O <sub>4</sub> ]	2	2	1	2	1	1	1	1	2	1	1	1	1	1	1	1	1	2	1	2	3	1	1	1
MEK [C <sub>4</sub> H <sub>8</sub> O]	4	4	3	2	2	2	3	3	3	3	3	3	3	3	3	3	3	2	2	3	4	4	3	2
Metan [CH <sub>4</sub> ]	2	2	2	1	1	1	1	2	2	1	2	2	2	2	2	2	2	1	1	1	2	1	1	1
Metanol [CH <sub>3</sub> OH]	3	3	3	2	2	2	3	3	3	3	3	3	3	3	3	3	3	2	2	4	3	3	2	2
Metylamín [CH <sub>3</sub> NH <sub>2</sub> ]	3	3	2	1	1	1	2	2	2	2	2	2	2	2	2	2	1	1	2	4	2	2	1	1
Metylenklorid [CH <sub>2</sub> Cl <sub>2</sub> ]	4	4	4	3	3	3	4	4	4	4	4	4	4	4	4	4	4	3	3	4	4	3	4	3
MIBK [C <sub>6</sub> H <sub>12</sub> O]	4	4	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	3	4	1	2	1
Mineralnafta	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1
Mjölksyra [C <sub>3</sub> H <sub>6</sub> O <sub>3</sub> ]	3	3	3	3	2	2	3	3	3	3	3	3	3	3	3	3	3	2	3	3	2	3	2	2
Monoetanolin [H <sub>2</sub> NCH <sub>2</sub> CH <sub>2</sub> OH]	3	3	3	2	2	2	3	3	3	3	3	3	3	3	3	3	3	2	3	3	2	3	2	2
Myrsyra(10%) [CH <sub>2</sub> O <sub>2</sub> ]	3	3	2	2	1	1	2	3	3	2	3	2	2	2	2	2	2	2	1	3	3	2	2	1
Nafta	1	1	1	1	1	1	1	2	2	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1
Natriumacetat [CH <sub>3</sub> COONa]	2	2	2	2	1	1	2	2	2	2	2	2	2	2	2	2	2	2	1	2	2	1	2	1
Natriumaluminat [AlNaO <sub>2</sub> ]	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1
Natriumbisulfat [NaHSO <sub>4</sub> ]	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1
Natriumbisulfit [Na <sub>2</sub> S <sub>2</sub> O <sub>5</sub> ]	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1
Natriumborat [Na <sub>2</sub> B <sub>4</sub> O <sub>7</sub> ]	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1
Natriumbromid [NaBr]	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1
Natriumcyanid [NaCN]	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	2	1	1	1
Natriumfluorid [NaF]	2	2	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	2	2	1	1	1
Natriumfosfat [NaH <sub>2</sub> PO <sub>4</sub> ]	2	2	2	1	1	1	2	2	2	2	2	2	2	2	2	2	2	1	1	2	2	1	1	1
Natriumhydroxid(10%) [NaOH]	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1
Natriumhydroxid(50%) [NaOH]	2	2	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	2	1	2	1
Natriumhypoklorit(6%) [NaClO]	1	1	1	1	1	1	1	3	1	1	1	1	1	1	1	1	1	1	1	1	2	1	1	1
Natriumkarbonat [Na <sub>2</sub> CO <sub>3</sub> ]	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1
Natriumklorat [NaClO <sub>3</sub> ]	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1

1= Continuous long term immersion  
2= Short term/intermittent immersion (<72 hrs.)

Chemical resistance Swedish.xls

3= Spills w/ immediate cleanup (<8 hrs.)  
4= Not recommended for direct contact



# Chemical Resistance Chart for ARC Composites

Ambient temperature and maximum concentration apply, unless otherwise noted

	S1	S1HB	S2	S3	S4+	982	SD4i	5	10	855	858	890	BX1	897	BX2	MX1	MX2	MX3	MX4	MX5	CS2	CS4	791	988
Natriumklorid [NaCl]	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1
Natriumkromat [Na <sub>2</sub> CrO <sub>4</sub> ]	2	2	2	2	1	1	2	2	2	2	2	2	2	2	2	2	2	1	1	2	2	1	2	1
Natriummetafosfat [(NaPO <sub>3</sub> ) <sub>n</sub> ]	2	2	2	1	1	1	2	2	2	2	2	2	2	2	2	2	2	1	1	2	2	1	1	1
Natriummetasilikat [Na <sub>2</sub> SiO <sub>3</sub> ]	2	2	2	1	1	1	2	2	2	2	2	2	2	2	2	2	2	1	1	2	2	1	1	1
Natriumnitrat [NaNO <sub>3</sub> ]	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1
Natriumsilikat [Na <sub>2</sub> SiO <sub>3</sub> ]	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1
Natriumsulfat [Na <sub>2</sub> SO <sub>4</sub> ]	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1
Natriumsulfit [Na <sub>2</sub> SO <sub>3</sub> ]	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1
Natriumvätekarbonat [NaHCO <sub>3</sub> ]	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1
Nickelammoniumsulfat [NiNH <sub>4</sub> SO <sub>4</sub> ]	2	2	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	2	1	1	1
Nickelklorid [NiCl <sub>2</sub> ]	2	2	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	2	1	1	2	1	1	1
Nickelnitrat [Ni(NO <sub>3</sub> ) <sub>2</sub> ]	2	2	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	2	1	1	1
Nickelsulfat [NiSO <sub>4</sub> ]	3	3	2	2	1	1	2	2	2	2	2	2	2	2	2	2	2	2	1	2	3	1	1	1
Nitrogen [N <sub>2</sub> ]	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1
Nitrogenoxid [NO]	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1
Oleum [rykande H <sub>2</sub> SO <sub>4</sub> ]	4	4	4	4	2	2	4	4	4	4	4	4	4	4	4	4	4	4	2	4	4	2	4	2
Oljesyra [C <sub>18</sub> H <sub>34</sub> O <sub>2</sub> ]	3	3	2	3	2	2	2	2	2	2	2	2	2	2	2	2	2	2	2	2	3	1	2	1
Palmitinsyra [CH <sub>3</sub> (CH <sub>2</sub> ) <sub>14</sub> COOH]	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1
Paraffin [C <sub>n</sub> H <sub>2n+2</sub> ]	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1
Petroleumnafta	2	2	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	2	2	1	1	1
Propylenoxid [C <sub>3</sub> H <sub>6</sub> O]	3	3	3	3	2	2	3	4	3	3	3	3	3	3	3	3	3	3	2	3	3	2	3	2
Rörsocker[C <sub>12</sub> H <sub>22</sub> O <sub>11</sub> ]	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1
Salpetersyra(10%) [HNO <sub>3</sub> ]	4	4	2	3	1	1	2	4	4	2	3	2	2	2	2	3	2	3	1	3	4	2	2	1
Salpetersyra(20%) [HNO <sub>3</sub> ]	4	4	3	4	2	2	3	4	4	3	3	3	3	3	3	3	3	3	2	4	4	3	3	2
Salpetersyra(60%) [HNO <sub>3</sub> ]	4	4	3	4	3	3	3	4	4	3	3	3	3	4	4	3	4	3	3	4	4	4	4	3
Saltlösning	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1
Saltsyra(10%) [HCl]	1	1	1	3	1	1	1	2	1	1	1	1	1	1	1	1	1	1	1	1	2	1	1	1
Saltsyra(37%) [HCl]	3	3	3	3	1	2	3	4	4	3	4	3	3	3	3	4	3	3	2	2	4	3	3	1
Saltvatten [NaCl+H <sub>2</sub> O+mineraler]	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1
Silikonolja	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1
Silvernitratt [AgNO <sub>3</sub> ]	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1
Skydrol [hydraulvätska till flygplan]	1	1	1	1	1	1	1	1	2	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1

1= Continuous long term immersion  
2= Short term/intermittent immersion (<72 hrs.)

Chemical resistance Swedish.xls

3= Spills w/ immediate cleanup (<8 hrs.)  
4= Not recommended for direct contact



# Chemical Resistance Chart for ARC Composites

Ambient temperature and maximum concentration apply, unless otherwise noted

	S1	S1HB	S2	S3	S4+	982	SD4i	5	10	855	858	890	BX1	897	BX2	MX1	MX2	MX3	MX4	MX5	CS2	CS4	791	988
Stärkelse [C6H12O6]n	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1
Svartlut	1	1	1	1	1	1	1	1	2	1	1	2	2	2	2	1	2	1	1	1	1	1	1	1
Svaveldioxid(torr) [SO2]	1	1	1	2	1	1	1	2	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1
Svavelsyra(10%) [H2SO4]	1	1	1	3	1	1	1	3	1	1	1	1	1	1	1	1	1	2	1	1	2	1	1	1
Svavelsyra(30%) [H2SO4]	4	4	3	3	1	1	3	4	3	3	3	3	3	3	3	3	3	3	1	4	4	1	3	1
Svavelsyra(70%) [H2SO4]	4	4	3	4	1	1	3	4	3	3	3	3	3	3	3	3	3	3	1	4	4	1	4	1
Svavelsyra(98%) [H2SO4]	4	4	3	4	1	1	3	4	3	3	3	3	3	3	3	3	3	3	1	4	4	1	4	1
Tennklorid [SnCl4]	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1
Terpentin [C10H16]	2	2	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	2	2	1	1	1
Tetraetylbly [Pb(C2H5)4]	2	2	2	1	1	1	2	2	2	2	2	2	2	2	2	2	2	1	1	2	2	1	1	1
Tjära	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1
Toluen [C7H8]	2	2	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	2	1	2	1
Transformatorolja	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	3	1	1	1
Trikloretan [CH3CCl3]	3	3	2	2	1	1	2	2	2	2	2	2	2	2	2	2	2	2	1	2	2	1	2	1
Väteperoxid(3%) [H2O2]	3	3	2	1	1	2	2	3	3	2	3	2	2	2	2	2	2	3	1	3	3	1	2	1
Vätesulfid(våt) [H2S]	2	2	1	2	1	1	1	1	2	1	1	2	2	2	2	1	2	1	1	2	3	1	1	1
Xylen [C6H4(CH3)2]	2	2	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	2	1	2	1
Zinkhydrosulfit [Zn(HSO3)2]	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1
Zinkklorid [ZnCl2]	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1
Zinksulfat [ZnSO4]	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1
Ättiksyra 5% [CH3COOH]	4	4	3	3	1	2	3	4	3	3	3	3	3	3	3	3	3	3	1	3	4	2	3	2
Öl	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1

1= Continuous long term immersion  
2= Short term/intermittent immersion (<72 hrs.)

Chemical resistance Swedish.xls

3= Spills w/ immediate cleanup (<8 hrs.)  
4= Not recommended for direct contact

I.



1= Continuous long term immersion  
2= Short term/intermittent immersion (<72 hrs.)

Chemical resistance Swedish.xls

3= Spills w/ immediate cleanup (<8 hrs.)  
4= Not recommended for direct contact

I.



1= Continuous long term immersion  
2= Short term/intermittent immersion (<72 hrs.)

Chemical resistance Swedish.xls

3= Spills w/ immediate cleanup (<8 hrs.)  
4= Not recommended for direct contact

I.



1= Continuous long term immersion  
2= Short term/intermittent immersion (<72 hrs.)

Chemical resistance Swedish.xls

3= Spills w/ immediate cleanup (<8 hrs.)  
4= Not recommended for direct contact

I.



1= Continuous long term immersion  
2= Short term/intermittent immersion (<72 hrs.)

Chemical resistance Swedish.xls

3= Spills w/ immediate cleanup (<8 hrs.)  
4= Not recommended for direct contact

I.



1= Continuous long term immersion  
2= Short term/intermittent immersion (<72 hrs.)

Chemical resistance Swedish.xls

3= Spills w/ immediate cleanup (<8 hrs.)  
4= Not recommended for direct contact

I.



1= Continuous long term immersion  
2= Short term/intermittent immersion (<72 hrs.)

Chemical resistance Swedish.xls

3= Spills w/ immediate cleanup (<8 hrs.)  
4= Not recommended for direct contact